

System specification

PROGEF Standard

Piping systems in polypropylene



The piping system with the completely controlled process

PROGEF Standard – System specification

Material	Material	Beta PP-H 100 (Beta Polypropylene Homopolymer) d16-d315mm PP-R (Random Copolymer) d355-d500mm
	Colour	RAL 7032 pebble grey
	Density	~0.90 g / cm ³ (ISO 1183 / ASTM D 792)
	Thermal expansion coefficient	0.16-0.18 mm / mK (DIN 53752)
	E-modulus	1300 N / mm ² (ISO 527 / ASTM D 790) 900 N / mm ² (ISO 527 / ASTM D 790)
	Thermal conductivity	0.23 W / mK (EN 12664)
	Surface resistivity	> 10 ¹⁶ Ω (IEC 60093)
	Dimension	d16-d500 in accordance to EN ISO 15494
Pressure rating	Pipes / fittings / diaphragm and ball valves	d16-d500 SDR11, PN10, c = 2.0 d50-d315 SDR17.6, PN6, c = 2.0
	Butterfly valves	d63-d225 PN10, d280-d315 PN 8
Temperature rating	From 0 °C to 80 °C (32 °F – 176 °F)	
Production	Fittings	Injection moulded or segment welded
	Pipes	Extruded
	Valves	Injection moulded
Product marking	All components are embossed with a permanent identification during the production process to ensure full traceability.	Lot No
		Material
		Dimension
		Pressure rating
Testing and inspection (EN ISO 15494)	Visual inspection	
	Surface finish	
	Dimension tolerance	
	Pressure testing	
	Full product range passed the Initial Type Test (ITT)	
Material- and product approvals / conformance ⁽¹⁾	FDA CFR 21 177.1520	
	USP 25 class VI (physiological non-toxic)	
	DIBt (Z-40.23-4, Z-40.34-264, Z – 40.23-265)	
	DNV (K-2630, K – 2636)	
	Lloyd's register (01 / 20030(E1))	
Fusion technology	Socket fusion (DVS 2207-11)	d16-d110
	IR Plus, infrared fusion (DVS 2207-6)	d20-d315
	Butt fusion (DVS 2207-11)	d20-d500
Documentation ⁽²⁾	EN 10204 2.2 / EN 10204 3.1	
Packaging	Pipes, fittings and valves bulk bagged	
Labeling	Brand name	
	Product description	
	Article number	
	Material	
	Dimension	
	Standards and approvals	
Main applications	PROGEF has been relied to be highly resistant to impact, abrasion and many chemicals. Suitable for industrial applications in chemical production, chemical distribution, galvanisation and power stations.	

⁽¹⁾ For the thermoplastic material only

⁽²⁾ On request

Contact

Georg Fischer Piping Systems Ltd
Ebnatstrasse 111
8201 Schaffhausen / Switzerland
Telephone +41 (0) 52 631 32 15

media.ps@georgfischer.com
www.gfps.com/media-center

The information and technical data (altogether "Data") herein are not binding, unless explicitly confirmed in writing. The Data neither constitutes any expressed, implied or warranted characteristics, nor guaranteed properties or a guaranteed durability. All Data is subject to modification. The General Terms and Conditions of Sale of Georg Fischer Piping Systems apply.

